

LINING FOILS

Application areas	Lining foils that can be sanded Ideal base for further paint coating in furniture construction
Supporting materials	■ Chipboard, MDF panels, wood materials or other planar substrates
Processing	 On flat heated, throughfeed, quickstep and double belt presses, as well hot/cold roller coating systems with all standard adhesives. When processing the foil from the roll, special equipment is required.
Pressure / processing temperature	■ Depending on the gluing system, feedspeed and press/dwell time Example: Press data for the hot press Temperature 90 - 160 °C Pressure 0,3 - 0,4 N/mm² Pressing time 50 - 10 sec The temperature of the processing material should never be below 20 °C.
Storage	■ In cool and dry rooms, in the original packaging (approx. 20 °C, 55-65 % air humidity), 6 months

1 www.ostermann.eu Stand: 9/2019