

## **Rakoll® Supermelt Professional I**

**Type of Adhesive**

Hot melt adhesive.

**Product Benefits**

- Medium open time
- High green strength
- Good adhesion properties and high tack
- High heat resistance

**Typical Applications**

Suitable for most types of edge materials which have been tested and approved by the substrate manufacturers for use with hot melt adhesive procedures. Specially suited for edgebanding with veneer and solid wood edges.

Also suitable for softforming application.

**Suitable substrates**

Edges of veneer and solid wood, melamine, HPL and thick plastic edges (PVC, ABS, PP ...), etc. to chipboard or MDF.

**Typical Properties**

| <b>Property</b>                   | <b>Value</b>                           |
|-----------------------------------|--|
| Base                              | Ethylene-vinyl acetate copolymer (EVA) |
| Softening point (R&B – ASTM E 28) | 110°C                                  |
| Viscosity (Brookfield HB)         | approx. 115 000 mPa.s at 204°C         |
| Shelf life                        | 12 months                              |



# H.B. Fuller



## TECHNICAL DATA SHEET

### Application Instructions

The machine should be adjusted according to the recommendations of the machine manufacturers.

Substrates should be perfectly clean and free of dust and grease.

#### Recommended working conditions:

- Ambient and substrate temperature: 18 – 20°C
- Wood moisture content: 8 – 10%
- Application temperature of the adhesive: 190 – 210°C
- Feeding speed: at least 15 m/min

Edges strips can have very different adhesion properties, even if the base material is the same. For this reason, it is advisable to make trials if the edges are of an unknown type in order to test the suitability of the adhesive. The recommendations given by the edge strip manufacturers should be followed.

During long stops, the adhesive temperature should be lowered to a temperature of 160°C to avoid degradation of the characteristics.

### Cleaning Instructions

All residual encrustations of adhesive must be completely cleaned from the melting tank from time to time as they conduct heat poorly and cause a lowering of the adhesive temperature.

### Typical Packaging

Please contact your local Sales Office for available packaging options.

### Storage Conditions

In original sealed packaging protected from sun, dust, moisture and high temperatures in clean and dry conditions.

### Disposal Advice

Please refer to the MSDS for disposal instructions.

### Safety Advice

At the recommended working temperature, the hot melt will cause burns in contact with skin. Do not inhale fumes that are released at the working temperature. In any case, a suitable exhausting system shall be installed in the working area.

Please refer to the MSDS for additional safety advices.

## Our Focus is Clear. Perfecting Adhesives.

**IMPORTANT:** The information, specifications, procedures and recommendations herein (together "information") are based on our experience and we believe these to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that the information will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.



## H.B. Fuller

**H.B. Fuller Company**

info-europe@hbfuller.com  
www.hbfuller.com/  
eimea/contact-us